

### PU-UF07

A Clear high gloss finish on both sides Poly Ether Urethane Thermo plastic film.  
Having no memory **PU-UF07** will not fracture as a result of constant flexing.

#### Advantages

- Superior flexibility
- Excellent abrasion resistance
- Clear Transparent high clarity
- Smooth welded seams
- Superior chemical resistance for CIP washing
- Great aging resistance
- Non porous
- Smooth surface
- No material degradation
- Smooth welded seam
- Excellent abrasion resistance
- CIP resistant
- 



#### Applications

Stationary, Vibratory, Gyrotory, Sifters, Screeners, Feeders, Spray driers, Fluid Bed, Static Cool Bed, Bin dischargers, Hoppers, Conveyors, Packing equipment, Storage silos, Screw conveyors, Valves, butterfly valves, Rotary valves, Tanks, Silo's, any sort of product handling equipment  
Air ducting , Fans, Inflatable seals, Covers, Outside protection sleeves, Bellows, Load cell (high volume, weight and capacity), Harmonica's, Telescopic applications, Vacuum formed shapes.

#### General Properties

<b>Name :</b>	PU-UF07
<b>Description :</b>	Poly Ether Urethane
<b>Color :</b>	Clear Transparent
<b>Surface :</b>	Gloss / Gloss (both sides)
<b>Surface Roughness :</b>	-
<b>Wall Thickness :</b>	0,70mm / 0.0275 Inch (+/-10%)
<b>Hardness :</b>	86° Shore A
<b>Tensile Strength :</b>	50 MPa
<b>Maximum Elongation :</b>	600%
<b>Operating Temperature :</b>	-40 °C to 90°C -40 °F to +194 °F
<b>Max. Surge Temp :</b>	+110 °C / +230 °F
<b>Low Temperature Flexibility :</b>	Good
<b>Air Permeability :</b>	0
<b>Type of Material :</b>	Sheet on roll, 1500x50000mm

#### Filcoflex B.V.

The Netherlands  
Luxemburgstraat 3  
5171 PK  
Kaatsheuvel

Website : [www.filcoflex.com](http://www.filcoflex.com)  
E-mail : [info@filcoflex.com](mailto:info@filcoflex.com)  
Telephone : +31 (0) 416 764 764  
Fax : +31 (0) 416 764 763

### Pressure Resistance for Flexible Connectors

---

0,2 Bar / 1.5 PSI For temperatures up to 90 °C / 195°F

Please see "Operating Pressure Guide" for further information.

we recommend using the shortest possible connector for applications where increased pressure and/or high temperature is expected. Please contact us for more information.

### Weighing Applications

---

High volume weight and capacity weighing and dosing applications please see "weighing and dosing guide" for further information.

### Chemical Resistance

---

- CIP resistant (see CIP chemicals guide)
- Cleaning Chemicals (see cleaning guide)
- For a detailed chemical resistance please see our chemical compatibility chart

### ATEX & Explosion Safety

---

**PU-UF07** has not yet been tested for its electrostatic properties, based on the testing of PU-UF1 and PU-UF03 it is safe to say PU-UF07 can be found ATEX compliant and safe to use in all dust explosion hazardous areas, such as ATEX zones 20, 21, 22, up to a maximum length of 100mm.\*



### Food Contact Compliancy

---

**PU-UF07** complies with the following regulations for plastics in repetitive contact with foods:\*

- **United States**
  - FDA 21 CFR 177.1680
- **European Community**
  - (EC) 1935/2004
  - (EC) 10/2011
  - (EC) 2019/1338
  - (EC) 2023-2006
  - (EC) 1907/2006 (REACH)
- **China**
  - GB 4806.7 – 2016
  - GB 5009.156
  - GB 31604.1 – 2015



\*Restrictions apply, a copy of all certifications can be downloaded, or will be sent to you upon request.  
We will be happy to advise further if you have any questions.

### Filcoflex B.V.

The Netherlands  
Luxemburgstraat 3  
5171 PK  
Kaatsheuvel

Website : [www.filcoflex.com](http://www.filcoflex.com)  
E-mail : [info@filcoflex.com](mailto:info@filcoflex.com)  
Telephone : +31 (0) 416 764 764  
Fax : +31 (0) 416 764 763

### Production Methods used

---

#### Joining / Bonding:

- Welding
  - HF high frequency welding  
Welding the material and cooling it down under compression with Radio Frequency to make the TPU material flow nearly seamless to form a uniform thickness with the original material wall thickness.
  - Heat contact – with silver alloy heating element  
Welds are welded surface to surface after which the weld are compressed while cooling.
  - Hot air – hot filtered and conditioned contaminant-, oil- and greas- free compressed air

#### Cutting :

- Stainless Steel knives
- Water Jet cutting